

ASTM A795 Standard Specification for Black and Hot-Dipped Galvanized Welded and seamless steel pipe for fire Protection Use

Schedule	Nominal Size	Outside Diameter	Wall Thickness	Mass of Black Tube	Test Pressure
	(inch)	(mm)	(mm)	Plain End (kg/m)	Grade B (PSI)
Schedule 10	3/4"	26.7	2.11	1.28	700
	1"	33.4	2.77	2.09	700
	1 1/4"	42.2	2.77	2.69	1000
	1 1/2"	48.3	2.77	3.11	1000
	2"	60.3	2.77	3.93	1000
	2 1/2"	73.0	3.05	5.26	1000
	3"	88.9	3.05	6.46	1000
	4"	114.3	3.05	8.37	1200
	5"	141.3	3.40	11.58	1200
	6"	168.3	3.40	13.85	1000
	8"	219.1	4.78	25.26	800
10"	273	4.78	31.62	700	
Schedule 40	1/2"	21.3	2.77	1.27	700
	3/4"	26.7	2.87	1.69	700
	1"	33.4	3.38	2.5	700
	1 1/4"	42.2	3.56	3.39	1300
	1 1/2"	48.3	3.68	4.05	1300
	2"	60.3	3.91	5.44	2500
	2 1/2"	73.0	5.16	8.63	2500
	3"	88.9	5.49	11.29	2500
	4"	114.3	6.02	16.07	2210
	5"	141.3	6.55	21.77	1950
	6"	168.3	7.11	28.26	1780
8"	219.1	8.18	42.55	1570	
10"	273	9.27	60.29	1430	

Note: Wall thickness tolerance is -12.5%